



ThinFlex

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Shiang, Kaohsiung County, 821, Taiwan, R.O.C.

(Kaohsiung Science Park)

Tel: +886-7-6955236 Fax: +886-7-6955539

http://www.thinflex.com.tw

e-mail: service@thinflex.com.tw

# ThinFlex A-1005RD Adhesiveless Double Sided Copper Clad Laminate (Halogen Free)

ThinFlex A-1005RD is an adhesiveless double-sided (D/S) copper clad laminate, using UBE TPI film and laminated with RA copper foil on both sides. ThinFlex A-1005RD adhesiveless D/S composites are designed for a wide variety of flexible circuit applications which require advanced material performance, temperature resistance, fine pitch, and high reliability.

## 1. Product Characteristics:

- \* Excellent dimensional stability
- \* Excellent flexibility
- \* Finer line etching capability
- \* Low moisture absorption
- \* Excellent flammability (Flame class UL 94V-0; UL File No. E219724)
- \* Excellent chemical resistance
- \* Excellent thermal, mechanical, and electrical properties

## 2. Specifications:

A - 10 05 R D

<b>Product</b> A : D/S FCCL	<b>Thickness of PI</b> 10 : 1.0 mil	<b>Thickness of Cu</b> 05 : 0.5 oz	<b>Cu Type</b> R : RA	<b>Structure</b> Double-sided
<b>Supply Size</b>	W: 250/500 ± 1mm; L: 400~700 ± 2mm (sheet type) W: 250/500 ± 1mm; L: 50 +2/-0m (roll type)			

\*Other thicknesses and dimensions are available on customers' demand.



ThinFlex

**ThinFlex Corporation**

No. 8, Luke 2nd.Rd., Luzhu Shiang, Kaohsiung County, 821, Taiwan, R.O.C.

(Kaohsiung Science Park)

Tel: +886-7-6955236 Fax: +886-7-6955539

<http://www.thinflex.com.tw>

e-mail: [service@thinflex.com.tw](mailto:service@thinflex.com.tw)

### 3. Construction:

Copper foil

Polyimide film

### 4. Properties:

Copper foil

Test item	Unit	A-1005RD	Test Method	
<b>Peel Strength</b>				
As Received	Kgf/cm	≥1.1	IPC-TM650 2.4.9 B	
Solder Float	Kgf/cm	≥1.1	IPC-TM650 2.4.13 B	
After Temp. Cycling	Kgf/cm	≥1.1	IPC-TM650 2.4.9	
Chemical Resistance	Kgf/cm	≥1.1	IPC-TM650 2.3.2	
Tensile Strength (Base Film)	Kg/mm <sup>2</sup>	31	IPC-TM-650 2.4.19	
Elongation (Base Film)	%	37	IPC-TM-650 2.4.19	
Tensile Modulus (Base Film)	Kg/mm <sup>2</sup>	500	ASTM D882	
Initial Tear Strength (Base Film)	g	860	IPC-TM-650 2.4.16	
Propagation Tear Strength (Base Film)	g	14	IPC-TM-650 2.4.17.1	
<b>Flexural Endurance, MIT</b>				
M.D.	Cycles	≥900	JIS-C 6471, 0.8mmR, 0.5kg	
T.D.	Cycles	≥900	JIS-C 6471, 0.8mmR, 0.5kg	
<b>Electrical Properties</b>				
Surface Resistance	Ω	~10 <sup>11</sup>	IPC-TM650 2.5.17	
Volume Resistance	Ω-cm	~10 <sup>12</sup>	IPC-TM650 2.5.17	
Insulation Resistance	Ω	~10 <sup>9</sup>	IPC-TM650 2.6.3.2	
Dielectric Strength	kV/mil	6.9	ASTM-D149	
Dielectric Constant	-	3.3	IPC-TM650 2.5.5.3	
Dissipation factor	-	0.002	IPC-TM650 2.5.5.3	
<b>Physical and Thermal Properties</b>				
Dimensional Stability	M.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
	T.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
CTE	ppm/°C	19.3	ThinFlex	
T <sub>g</sub>	°C	350	ThinFlex	
Solder Float	10sec at 288°C (550°F)	-	Pass	IPC-TM650 2.4.13
Moisture Absorption Test	%	1.1	IPC-TM650 2.6.2	
Chemical Resistance-single	-	Pass	IPC-TM650 2.3.2	
Thickness tolerance	um	61±10%	ThinFlex	
UL Flame Class	-	94V-0	UL	

\* Above data are typical values, and are not guaranteed values.

Technical Data Sheet: 201104



ThinFlex

## ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Shiang, Kaohsiung County, 821, Taiwan, R.O.C.

(Kaohsiung Science Park)

Tel: +886-7-6955236 Fax: +886-7-6955539

<http://www.thinflex.com.tw>

e-mail: [service@thinflex.com.tw](mailto:service@thinflex.com.tw)

## 5. Storage:

ThinFlex A-1005RD will meet its shelf-life for at least 12 months after arrival at the user's factory when stored in the original packaging at temperatures of below 25°C and below 70% humidity. The products do not need refrigeration and should not be frozen.

Note: The information and data contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

## ThinFlex Corporation

No.8, Luke 2<sup>nd</sup> Rd., Luzhu Shiang, Kaohsiung County 821, Taiwan, R.O.C. (Kaohsiung Science Park)

Tel: +886-7-6955236 Fax: +886-7-6955539

<http://www.thinflex.com.tw>

e-mail: [service@thinflex.com.tw](mailto:service@thinflex.com.tw)